



**WASH PRIMER 2035-534 ROHS COMPLIANT**

GENERAL INFORMATION	PHYSICAL PROPERTIES	APPLICATION
<p>A two component vinyl based, acid etch wash primer specifically designed as an adhesion promoter for topcoat paint systems over untreated ferrous and non ferrous substrates.</p> <p>This product is recommended for use with polyurethanes, baking enamels and lacquers in order to promote adhesion.</p> <p>Eastern Chem Lac warrants that its products meet its internal specifications and are of merchantable quality. However, the purchaser is solely responsible for the suitability of the product for any particular application. The purchaser should thoroughly test or qualify the product for serviceability, environmental compliance and health and safety factors prior to use. Further, our total liability is limited to the price of the product or replacement in kind.</p> <p>Eastern Chem Lac  33 Haynes Circle  Chicopee, MA 01020  Phone: 413-592-6997  Fax: 413-594-7321  www.eclcoatings.com</p>	<ol style="list-style-type: none"> <li><b>1. Volume Solids:</b> 4.2 +/- 0.2%</li> <li><b>2. Theoretical Coverage @ 1 mil dft:</b> 67 ft<sup>2</sup>/gallon</li> <li><b>3. Dry Time:</b> Set to Touch: 5 minutes To Handle: 10 – 15 minutes To Topcoat: 20 - 30 minutes Force Dry @ 150 – 180°F: Dry to Topcoat: 10 minutes</li> <li><b>4. Dry Film Thickness:</b> 0.2 – 0.4 mils</li> <li><b>5. Mix Ratio:</b> 1 part 2035-534 1 part X2649 Wash Primer Reducer Mix well before use.</li> <li><b>6. VOC:</b> 6.5 lbs/gallon (777 grams/liter)</li> <li><b>7. Pot Life:</b> 8 hours</li> <li><b>8. Shelf Life:</b> One Year</li> </ol>	<p>Can be applied using conventional air, airless, or HVLP.</p> <p><b>Substrate Preparation:</b> Substrate must be clean and free of oils, grease, dirt or other contaminants prior to application. Apply a smooth wet film to the cleaned substrate.</p> <p><b>Clean-Up:</b> 928 Washing Thinner or T4-1 Lacquer Thinner.</p> <p><b>Safety Precautions:</b> This product is intended for professional use in an industrial environment only. Consult the Material Safety Data Sheet prior to application.</p>